



## CODE APPLICATION NOTICE (CAN)

CAN: 2-703.2

H&S Code §129851

### SUBJECT

Rebar in Lieu of Welded Wire Fabric in Fire-Resistance-Rated Assemblies

**Effective:** 05/18/2009

**Revised:** 02/28/2023



### CODE SECTIONS

Sections 703.2 and 703.2.2  
2022 California Building Code (CBC)

2022 California Building Code

**703.2 Fire-resistance.** The fire-resistance rating of building elements, components or assemblies shall be determined in accordance with Section 703.2.1 or 703.2.2 without the use of automatic sprinklers or any other fire suppression system being incorporated, or in accordance with Section 703.2.3.

...

**703.2.2 Analytical methods.** The fire resistance of a building elements, components or assemblies established by an analytical method shall be by any of the methods listed in this section, based on the fire exposure and acceptance criteria specified in ASTM E119 or UL 263.

1. Fire-resistance designs documented in approved sources.
2. Prescriptive designs of fire-resistance-rated building elements, components or assemblies as prescribed in Section 721.
3. Calculations in accordance with Section 722.
4. Engineering analysis based on a comparison of building element, component or assemblies designs having fire-resistance ratings as determined by the test procedures set forth in ASTM E119 or UL 263.
5. Fire-resistance designs certified by an approved agency.

...

### PURPOSE

The purpose of this Code Application Notice is to clarify when rebar may be used in lieu of welded wire fabric in fire-rated concrete floor-ceiling assemblies.

## **BACKGROUND**

Fire-resistance-rated concrete floor-ceiling assemblies are tested by independent laboratories and assigned a fire-resistance-rating based on the specific components of the tested assembly. The testing laboratory is required to comply with the testing procedures of ASTM E 119. Where materials that have not been tested as part of a fire-resistance-rated assembly are incorporated into the assembly, sufficient data shall be made available to the building official to show that the required fire-resistance-rating is not reduced. Many fire-resistance-rated concrete floor assemblies use welded wire fabric. Steel reinforcing bar (rebar) is a common alternative to welded wire fabric and is often required for the structural design of the building. Rebar is preferred by the structural engineering community because it has greater strength and better structural performance than welded wire fabric. Although rebar may be desirable for structural reasons, few assemblies have been tested with rebar.

ASTM E 2032 Standard Guide for Extension of Data from Fire Endurance Tests conducted in accordance with ASTM E119 covers the extension of fire endurance results obtained from tests performed in accordance with ASTM E 119 to constructions that have not been tested. The guide is based on principles involving the extension of test data using simple considerations and its application is based substantially on an analogous worst case scenario. Under the discussion of Principles Pertaining to Heat Transfer Characteristics of Concrete, the standard states “for concrete test specimens where temperature rise on the unexposed surfaces is the governing criterion, changes in the type or amount of reinforcement does not reduce the fire endurance of the assembly.” Under the discussion of Principles Pertaining to Fire Endurance of Floor or Roof Ceiling Assemblies, the standard affirms that “for concrete slab assemblies where temperature rise on the unexposed surface of a concrete slab is a governing criterion, (that is, the structural design requirements are met and adequate cover protection is provided to the steel reinforcement [prestressing and reinforcing bars]), modifications in the concrete materials used, concrete mixture, or slab designs (described in Section 6) do not reduce the fire endurance.”

## **INTERPRETATION**

California Building Code Section 722 contains procedures by which the fire resistance of specific materials or combinations of materials is established by calculations; Section 722.2.2 contains the provisions for calculating the fire resistance of reinforced and prestressed concrete floor and roof slabs.

In accordance with Section 722.2.3.1, the minimum thickness of concrete cover to the positive moment reinforcement shall comply with Table 722.2.3(1) for reinforced concrete. This table is applicable to slabs that are either cast in place or precast.

**TABLE 722.2.3(1)**  
**COVER THICKNESS FOR REINFORCED CONCRETE FLOOR OR ROOF SLABS (inches)**

CONCRETE AGGREGATE TYPE	FIRE-RESISTANCE RATING (hours)									
	Restrained					Unrestrained				
	1	1½	2	3	4	1	1½	2	3	4
Siliceous	¾	¾	¾	¾	¾	¾	¾	1	1¼	1½
Carbonate	¾	¾	¾	¾	¾	¾	¾	¾	1¼	1½
Sand-lightweight or lightweight	¾	¾	¾	¾	¾	¾	¾	¾	1¼	1½

For SI: 1 inch = 25.4 mm.

For fire-resistance-rated concrete floor assemblies tested with welded wire mesh fabric, steel reinforcing bars (rebar) may be substituted for welded wire mesh if the minimum cover thickness for the reinforcing bars is at least as thick as the values shown in Table 722.2.3(1). An Engineering Judgment or an Alternate Method of Protection will not be required if the plans clearly detail the installation of all reinforcing bars and the relationship of the concrete cover thickness to the reinforcing bars.

Original signed	2/28/2023
Chris Tokas	Date